

# CapaLite



High quality internal wall paint, for all kinds of interior delicate decoration.



## Properties /

## Product Description

- ▶ A variety of color options according to the 3D colour card.
- ▶ Dry paint film is easy to clean.
- ▶ The lacquer film is exquisite and full, the color is bright and persistent.
- ▶ Good opacity (first-class according to GB/T 9756-2009 synthetic resin emulsion interior wall coating).
- ▶ Good smell, meet environmental protection requirements.

## Usage /

Specially for all kinds of fine decoration apartment interior wall decoration, suitable for residential, hotel, school, office buildings and other kinds of projects. A surface treatment wall, as a beautification and protection of the wall.

## Tech data / Ingredients

Acrylic emulsion, titanium dioxide, extenders, pigments, additives and deionized water.

Gloss level	Matte to low light, depending on the colour
Theoretical coverage	10 m <sup>2</sup> /L/Coat
Drying time	Surface dry : 1hr (Air temperature: 23°C, Relative humidity: 50%) Recoat : 4hr (Air temperature : 23°C, Relative humidity: 50%)
Volume solid	42%
Density	1.57 kg/L (influence proportion after color mixing)
Weather Resistance	Good
Safety	No added Pb and Hg
Colour	White, colour-adjustable (according to 3D colour card)
<b>Applications /</b> Tools	Paint brush, roller, spray gun
Thinner	Dilute with clear water, dilute ratio of 5-10%
Wet film thickness	Theoretical value: about 100 microns (1 coat)
Dry film thickness	Theoretical value: about 42 microns (1 coat)
Conditions	Air temperature: > 8°C , Relative humidity: <85%
Cleaning	Rinse with fresh water immediately after application
Notes	Don't apply under direct sunlight

## Packing /

15L

## Storage /

Keep in cool and dry place, avoid from frost

## Application

Surface preparations / Interior wall putty	1.Putty completely dry, grinding with fine sandpaper to remove dust 2.If the request is more durable, brush the diluted CapaSol SF before scraping the putty. 3.Putty should not be too soft.
Powdered surface	1.Remove dust as much as possible. 2.Brush the diluted CapaSol SF.
Moldy surface	1. Wipe the mold. 2. Brush again wash water, to be dry 24-48 hours, brush once again dilute the Dragon Fort seal primer.
Method of application /	a. Read the instruction before application. b. Stir well before applying. c. Follow the instructions to add a proper amount of water. Do not overdose and stir evenly. d. Avoid over loading of paints on tools. e. Wash tools immediately after applications f. Do not fill the thinned paints into the packing drum.
Painting system /	CapaPrimer(1 coat)+CapaLite(1 coat)

## Advice

<b>SHE /</b>	This product conforms to the National Standard GB/T9756-2009 "synthetic resin emulsion interior wall paint" (first class), GB18582-2008 "indoor decoration decoration material inside wall coating harmful material limit" (water - based wall Coating) It is our principle to provide high standard of safety, health and environmental information. We will provide materials safety data free of charge as well as related information.
<b>Information /</b>	1. Please follow BS6150:1991 standard for architectural coating applications and BS8000:1989 for site instruction. 2. Shelf life : 24 months in unopened condition. 3. Above information is provided by Caparol (China) Ltd, we ensure the accuracy of the information provided. However due to the application conditions are not controllable, there may be variance in end result. 4. For further enquiry, please contact our company. Please make sure the information is updated before application. The above information was released in Jan 2018. Caparol (China) Ltd. reserve the right to update the above information without notice in advance.
<b>Trademark declaration / Company address /</b>	Caparol is the trademarks belong to DAW SE. CAPAROL (CHINA) LTD. 25F, Block B Kingboard Square, 505 Guangming Road, Huaqiao Economic Development Zone, Kunshan, Jiangsu, 215332
<b>Tel /</b>	0512-86183333
<b>Fax /</b>	0512-86183311
	<a href="http://www.dawchina.com">www.dawchina.com</a>