



# CapaMarble Pattern

Artificial natural stone effect waterborne art paint, seamless stone decoration effect, set beautiful and protective.



## Properties /

## Product Description

- ▶ Artificial all kinds of different texture stone, high decorative effect.  
Strong weatherability, protecting the wall.
- ▶ Inorganic pigment blending, high colour range.
- ▶ Resistance to alkali and modly.
- ▶ Water based technology.

## Usage /

It is used for all kinds of advanced apartments, villas, holiday hotels, theme parks, schools, art galleries, etc.

## Tech data / Ingredients

Acrylic copolymer, extenders, additives and deionized water.

Gloss level

Low gloss

Theoretical coverage

0.3-0.8kg/ m<sup>2</sup> (usage will be affected by the pattern effect)

Drying time

Surface dry : 2-4hr (Air temperature: 23°C, Relative humidity: 50%)

Recoat : 24hr (Air temperature : 23°C, Relative humidity: 50%)

Volume solid

40%

Density

1.5 kg/L

Weather Resistance

Good

Safety

No added Pb and Hg

Colour

refer to the colour card

## Applications / Tools

Professional spray gun (for example, model w-871), nozzle caliber 2.5mm-3.5mm

Thinner

Not necessary

Wet film thickness

Theoretical value: abou 400 microns (1 coat)

Dry film thickness

Theoretical value: about 160 microns (1 coat)

Conditions

Air temperature: > 8°C , Relative humidity: <85%

Cleaning

Rinse with fresh water immediately after application

Notes

Don't apply under direct sunlight

## Packing /

20KG

## Storage /

Keep in cool and dry place, avoid from frost

## Application

Surface preparations /  
New substrate

1. New concrete must be maintained for 30 days.
2. Remove the looseness and crystal salt.
3. Fill the fissure and trap with appropriate filler.
4. The surface should be clean before application.

Powdered surface

1. Remove dust as much as possible.
2. Brush the diluted CapaSol SF.

Moldy surface

1. Wipe the mold.
2. Brush again wash water, to be dry 24-48 hours, brush once again dilute the Dragon Fort seal primer.

Method of application /

- a. Read the instruction before application.
- b. Stir well before applying.
- c. Air source pressure is controlled at 0.6-0.8 MPa.
- d. Pressure control of material can be controlled at 0.1%-0.15mpa, using point spray method, and after drying, the standard sample is compared, and the pattern density is sparse.
- e. Wash tools immediately after applications
- f. Do not fill the thinned paints into the packing drum.

Painting system /

Primer:	CapaSeal	Roller	(1 coat)
Mid-coat:	CapaMarble Base	Roller	(2 coat)
Main material:	CapaMarble Pattern	Spray	(1 coat)
Finish:	CapaGlaze G	Spray or Roller	(1 coat)

## Advice

**Please Note /**

1. The actual coverage will be smoothness of the wall, and the pattern will be selected. Please call our company if you have any questions.

**SHE /**

2. The surface of lime cement mortar must be brushed with deboron seal.

This product meets the National Standard HG/T4343-2012.

It is our principle to provide high standard of safety, health and environmental information. We will provide materials safety data free of charge as well as related information.

**Information /**

1. Please follow BS6150:1991 standard for architectural coating applications and BS8000:1989 for site instruction.

2. Shelf life : 24 months in unopened condition.

3. Above information is provided by Caparol (China) Ltd, we ensure the accuracy of the information provided. However due to the application conditions are not controllable, there may be variance in end result.

4. For further enquiry, please contact our company. Please make sure the information is updated before application. The above information was released in Jan 2018. Caparol (China) Ltd. reserve the right to update the above information without notice in advance.

**Trademark declaration /  
Company address /**

Caparol is the trademarks belong to DAW SE.

CAPAROL (CHINA) LTD.

25F, Block B Kingboard Square, 505 Guangming Road,  
Huaqiao Economic Development Zone, Kunshan, Jiangsu, 215332

**Tel /**

0512-86183333

**Fax /**

0512-86183311

www.dawchina.com